

BÖHLER 2.5 Ni-IG medium alloy TIG wire

Medium Alloy wire by about 2.5% Ni for the welding of fine grain steel and nickel alloys. Good impact toughness at low temperatures down to -80 ° C.



Diameter mm	ISO standard	AWS standard	Article
2	W2Ni2	ER 80S-Ni2	12575149
2.4	W2Ni2	ER 80S-Ni2	12575150

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.