BÖHLER FOX ASN 5-A high alloyed electrodes



Rutile coated electrode for arc welding of Cr-Ni steel with a relatively high molybdenum content such as 317L. Particularly good resistance to stress corrosion, crevice and pitting corrosion. PRE = 36

Diameter	Total length	ISO standard	AWS standard	Packaging	Article
mm	mm				
2.5	300	E 18 16 5 N L R 3 2	E 317L-17	195	12574958
3.2	350	E 18 16 5 N L R 3 2	E 317L-17	120	12574959

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

Page 1/1

