



BÖHLER FOX CM 2 Kb medium alloyed electrodes

Basic coated electrode for welding creep resistant steels as 10CrMo9.10 used in high-temperature-resistant components of tank equipment construction, pipelines and petroleum industries. Operating temperatures up to +600 ° C.

Diameter mm	Total length mm	ISO standard	AWS standard	Packaging	Article
2.5	250	E CrMo2 B 42 H5	E 9018-B3 H4 R	195	12574892
3.2	350	E CrMo2 B 42 H5	E 9018-B3 H4 R	130	12574893
4	350	E CrMo2 B 42 H5	E 9018-B3 H4 R	85	12574894

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.