



FESTO Plastic tubing PUN-H

Characteristics

Series: PUN-H

Hose material: TPE-U(PU)

Internal diameter	Wall thickness	Outer diameter	Maximum operating pressure at 20 °C	Roller length	Colour	Minimum bending radius	FDA quality mark	Hardness	Weight per meter	Article
mm	mm	mm	bar	m		mm			g	
1.2	0.4	2	10	50	Black	5	Yes	D 52 +/-3	2.4	13206372
2.1	0.5	3	10	50	Black	6	Yes	D 52 +/-3	4.2	11639940
2.1	0.5	3	10	500	Black	6	Yes	D 52 +/-3	4.2	12264995
2.1	0.5	3	10	500	Blue	6	Yes	D 52 +/-3	4.2	12265002
2.1	0.5	3	10	50	Blue	6	Yes	D 52 +/-3	4.2	11639938
2.1	0.5	3	10	50	Green	6	Yes	D 52 +/-3	4.2	11651480
2.1	0.5	3	10	50	Natural	6	Yes	D 52 +/-3	4.2	11639933
2.1	0.5	3	10	500	Natural	6	Yes	D 52 +/-3	4.2	12265009
2.1	0.5	3	10	50	Red	6	Yes	D 52 +/-3	4.2	11651477
2.1	0.5	3	10	50	Silver	6	Yes	D 52 +/-3	4.2	11651474
2.1	0.5	3	10	500	Silver	6	Yes	D 52 +/-3	4.2	12265016
2.1	0.5	3	10	50	Yellow	6	Yes	D 52 +/-3	4.2	11651483
2.6	0.75	4	10	50	Black	8	Yes	D 52 +/-3	8.5	11639941
2.6	0.75	4	10	25	Black	8	Yes	D 52 +/-3	8.5	14153957
2.6	0.75	4	10	500	Black	8	Yes	D 52 +/-3	8.5	12264996
2.6	0.75	4	10	500	Blue	8	Yes	D 52 +/-3	8.5	12265003
2.6	0.75	4	10	25	Blue	8	Yes	D 52 +/-3	8.5	14153933
2.6	0.75	4	10	50	Blue	8	Yes	D 52 +/-3	8.5	23213042
2.6	0.75	4	10	50	Green	8	Yes	D 52 +/-3	8.5	11651481
2.6	0.75	4	10	50	Natural	8	Yes	D 52 +/-3	8.5	23212994
2.6	0.75	4	10	500	Natural	8	Yes	D 52 +/-3	8.5	12265010
2.6	0.75	4	10	50	Red	8	Yes	D 52 +/-3	8.5	11651478
2.6	0.75	4	10	50	Silver	8	Yes	D 52 +/-3	8.5	11651475
2.6	0.75	4	10	500	Silver	8	Yes	D 52 +/-3	8.5	12265017
2.6	0.75	4	10	25	Transparent black	8	Yes	D 52 +/-3	8.5	14153964
2.6	0.75	4	10	50	Transparent black	8	Yes	D 52 +/-3	8.5	14170029
2.6	0.75	4	10	500	Transparent black	8	Yes	D 52 +/-3	8.5	14170028
2.6	0.75	4	10	25	Transparent blue	8	Yes	D 52 +/-3	8.5	14153938
2.6	0.75	4	10	500	Transparent blue	8	Yes	D 52 +/-3	8.5	13206731
2.6	0.75	4	10	50	Transparent blue	8	Yes	D 52 +/-3	8.5	13206730
2.6	0.75	4	10	50	Transparent green	8	Yes	D 52 +/-3	8.5	14170011
2.6	0.75	4	10	500	Transparent green	8	Yes	D 52 +/-3	8.5	14170010
2.6	0.75	4	10	25	Transparent green	8	Yes	D 52 +/-3	8.5	14153949
2.6	0.75	4	10	25	Transparent red	8	Yes	D 52 +/-3	8.5	14153954
2.6	0.75	4	10	50	Transparent red	8	Yes	D 52 +/-3	8.5	14170020

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

Internal diameter	Wall thickness	Outer diameter	Maximum operating pressure at 20 °C	Roller length	Colour	Minimum bending radius	FDA quality mark	Hardness	Weight per meter	Article
mm	mm	mm	bar	m		mm			g	
2.6	0.75	4	10	500	Transparent red	8	Yes	D 52 +/-3	8.5	14170019
2.6	0.75	4	10	50	Transparent yellow	8	Yes	D 52 +/-3	8.5	14170001
2.6	0.75	4	10	500	Transparent yellow	8	Yes	D 52 +/-3	8.5	14170000
2.6	0.75	4	10	25	Transparent yellow	8	Yes	D 52 +/-3	8.5	14153944
2.6	0.75	4	10	50	Yellow	8	Yes	D 52 +/-3	8.5	11651484
4	1	6	10	50	Black	10	Yes	D 52 +/-3	18.3	11639942
4	1	6	10	25	Black	10	Yes	D 52 +/-3	18.3	14153958
4	1	6	10	500	Black	10	Yes	D 52 +/-3	18.3	12264997
4	1	6	10	500	Blue	10	Yes	D 52 +/-3	18.3	12265004
4	1	6	10	25	Blue	10	Yes	D 52 +/-3	18.3	14153934
4	1	6	10	50	Blue	10	Yes	D 52 +/-3	18.3	23213024
4	1	6	10	50	Green	10	Yes	D 52 +/-3	18.3	11651482
4	1	6	10	50	Natural	10	Yes	D 52 +/-3	18.3	23213008
4	1	6	10	500	Natural	10	Yes	D 52 +/-3	18.3	12265011
4	1	6	10	50	Red	10	Yes	D 52 +/-3	18.3	11651479
4	1	6	10	50	Silver	10	Yes	D 52 +/-3	18.3	11651476
4	1	6	10	500	Silver	10	Yes	D 52 +/-3	18.3	12265018
4	1	6	10	25	Transparent black	10	Yes	D 52 +/-3	18.3	14153965
4	1	6	10	50	Transparent black	10	Yes	D 52 +/-3	18.3	14170031
4	1	6	10	500	Transparent black	10	Yes	D 52 +/-3	18.3	14170030
4	1	6	10	25	Transparent blue	10	Yes	D 52 +/-3	18.3	14153939
4	1	6	10	50	Transparent blue	10	Yes	D 52 +/-3	18.3	13206732
4	1	6	10	500	Transparent blue	10	Yes	D 52 +/-3	18.3	13206733
4	1	6	10	25	Transparent green	10	Yes	D 52 +/-3	18.3	14153950
4	1	6	10	50	Transparent green	10	Yes	D 52 +/-3	18.3	14170013
4	1	6	10	500	Transparent green	10	Yes	D 52 +/-3	18.3	14170012
4	1	6	10	50	Transparent red	10	Yes	D 52 +/-3	18.3	13708928
4	1	6	10	500	Transparent red	10	Yes	D 52 +/-3	18.3	14170021
4	1	6	10	25	Transparent red	10	Yes	D 52 +/-3	18.3	14153955
4	1	6	10	25	Transparent yellow	10	Yes	D 52 +/-3	18.3	14153945
4	1	6	10	50	Transparent yellow	10	Yes	D 52 +/-3	18.3	14170003
4	1	6	10	500	Transparent yellow	10	Yes	D 52 +/-3	18.3	14170002
4	1	6	10	50	Yellow	10	Yes	D 52 +/-3	18.3	11651485
5.7	1.25	8	10	50	Black	21	Yes	D 52 +/-3	28.7	11639943
5.7	1.25	8	10	25	Black	21	Yes	D 52 +/-3	28.7	14153961
5.7	1.25	8	10	400	Black	21	Yes	D 52 +/-3	28.7	12264998
5.7	1.25	8	10	400	Blue	21	Yes	D 52 +/-3	28.7	12265005
5.7	1.25	8	10	25	Blue	21	Yes	D 52 +/-3	28.7	14153935
5.7	1.25	8	10	50	Blue	21	Yes	D 52 +/-3	28.7	23212981
5.7	1.25	8	10	50	Green	21	Yes	D 52 +/-3	28.7	12265030
5.7	1.25	8	10	400	Natural	21	Yes	D 52 +/-3	28.7	12265012

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

Internal diameter	Wall thickness	Outer diameter	Maximum operating pressure at 20 °C	Roller length	Colour	Minimum bending radius	FDA quality mark	Hardness	Weight per meter	Article
mm	mm	mm	bar	m		mm			g	
5.7	1.25	8	10	50	Natural	21	Yes	D 52 +/-3	28.7	11639934
5.7	1.25	8	10	50	Red	21	Yes	D 52 +/-3	28.7	12265026
5.7	1.25	8	10	400	Silver	21	Yes	D 52 +/-3	28.7	12265019
5.7	1.25	8	10	50	Silver	21	Yes	D 52 +/-3	28.7	24212172
5.7	1.25	8	10	25	Transparent black	21	Yes	D 52 +/-3	28.7	14153966
5.7	1.25	8	10	50	Transparent black	21	Yes	D 52 +/-3	28.7	14170033
5.7	1.25	8	10	400	Transparent black	21	Yes	D 52 +/-3	28.7	14170032
5.7	1.25	8	10	400	Transparent blue	21	Yes	D 52 +/-3	28.7	13206735
5.7	1.25	8	10	25	Transparent blue	21	Yes	D 52 +/-3	28.7	14153940
5.7	1.25	8	10	50	Transparent blue	21	Yes	D 52 +/-3	28.7	13206734
5.7	1.25	8	10	25	Transparent green	21	Yes	D 52 +/-3	28.7	14153951
5.7	1.25	8	10	50	Transparent green	21	Yes	D 52 +/-3	28.7	14170015
5.7	1.25	8	10	400	Transparent green	21	Yes	D 52 +/-3	28.7	14170014
5.7	1.25	8	10	50	Transparent red	21	Yes	D 52 +/-3	28.7	14170023
5.7	1.25	8	10	400	Transparent red	21	Yes	D 52 +/-3	28.7	14170022
5.7	1.25	8	10	25	Transparent red	21	Yes	D 52 +/-3	28.7	14153956
5.7	1.25	8	10	25	Transparent yellow	21	Yes	D 52 +/-3	28.7	14153946
5.7	1.25	8	10	50	Transparent yellow	21	Yes	D 52 +/-3	28.7	14170005
5.7	1.25	8	10	400	Transparent yellow	21	Yes	D 52 +/-3	28.7	14170004
5.7	1.25	8	10	50	Yellow	21	Yes	D 52 +/-3	28.7	12265034
7	1.5	10	10	300	Black	28	Yes	D 52 +/-3	46.5	12264999
7	1.5	10	10	50	Black	28	Yes	D 52 +/-3	46.5	11639944
7	1.5	10	10	50	Blue	28	Yes	D 52 +/-3	46.5	23213041
7	1.5	10	10	300	Blue	28	Yes	D 52 +/-3	46.5	12265006
7	1.5	10	10	50	Green	28	Yes	D 52 +/-3	46.5	12265031
7	1.5	10	10	300	Natural	28	Yes	D 52 +/-3	46.5	12265013
7	1.5	10	10	50	Natural	28	Yes	D 52 +/-3	46.5	11639935
7	1.5	10	10	50	Red	28	Yes	D 52 +/-3	46.5	12265027
7	1.5	10	10	300	Silver	28	Yes	D 52 +/-3	46.5	12265020
7	1.5	10	10	50	Silver	28	Yes	D 52 +/-3	46.5	12265023
7	1.5	10	10	300	Transparent black	28	Yes	D 52 +/-3	46.5	14170034
7	1.5	10	10	50	Transparent black	28	Yes	D 52 +/-3	46.5	14170035
7	1.5	10	10	25	Transparent black	28	Yes	D 52 +/-3	46.5	14153962
7	1.5	10	10	25	Transparent blue	28	Yes	D 52 +/-3	46.5	14153936
7	1.5	10	10	300	Transparent blue	28	Yes	D 52 +/-3	46.5	13206737
7	1.5	10	10	50	Transparent blue	28	Yes	D 52 +/-3	46.5	13206736
7	1.5	10	10	300	Transparent green	28	Yes	D 52 +/-3	46.5	14170016
7	1.5	10	10	50	Transparent green	28	Yes	D 52 +/-3	46.5	14170017
7	1.5	10	10	25	Transparent green	28	Yes	D 52 +/-3	46.5	14153947

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

Internal diameter	Wall thickness	Outer diameter	Maximum operating pressure at 20 °C	Roller length	Colour	Minimum bending radius	FDA quality mark	Hardness	Weight per meter	Article
mm	mm	mm	bar	m		mm			g	
7	1.5	10	10	25	Transparent red	28	Yes	D 52 +/-3	46.5	14153952
7	1.5	10	10	50	Transparent red	28	Yes	D 52 +/-3	46.5	14170025
7	1.5	10	10	300	Transparent red	28	Yes	D 52 +/-3	46.5	14170024
7	1.5	10	10	300	Transparent yellow	28	Yes	D 52 +/-3	46.5	14170006
7	1.5	10	10	50	Transparent yellow	28	Yes	D 52 +/-3	46.5	14170007
7	1.5	10	10	25	Transparent yellow	28	Yes	D 52 +/-3	46.5	14153942
7	1.5	10	10	50	Yellow	28	Yes	D 52 +/-3	46.5	12265035
8	2	12	10	200	Black	33	Yes	D 52 +/-3	72.9	12265000
8	2	12	10	50	Black	33	Yes	D 52 +/-3	72.9	11639945
8	2	12	10	50	Blue	33	Yes	D 52 +/-3	72.9	23213025
8	2	12	10	200	Blue	33	Yes	D 52 +/-3	72.9	12265007
8	2	12	10	50	Green	33	Yes	D 52 +/-3	72.9	12265032
8	2	12	10	200	Natural	33	Yes	D 52 +/-3	72.9	12265014
8	2	12	10	50	Natural	33	Yes	D 52 +/-3	72.9	11639936
8	2	12	10	50	Red	33	Yes	D 52 +/-3	72.9	12265028
8	2	12	10	50	Silver	33	Yes	D 52 +/-3	72.9	12265024
8	2	12	10	200	Silver	33	Yes	D 52 +/-3	72.9	12265021
8	2	12	10	50	Transparent black	33	Yes	D 52 +/-3	72.9	14170037
8	2	12	10	200	Transparent black	33	Yes	D 52 +/-3	72.9	14170036
8	2	12	10	25	Transparent black	33	Yes	D 52 +/-3	72.9	14153963
8	2	12	10	50	Transparent blue	33	Yes	D 52 +/-3	72.9	13206738
8	2	12	10	200	Transparent blue	33	Yes	D 52 +/-3	72.9	13206739
8	2	12	10	200	Transparent green	33	Yes	D 52 +/-3	72.9	14170018
8	2	12	10	25	Transparent green	33	Yes	D 52 +/-3	72.9	14153948
8	2	12	10		Transparent green	33	Yes	D 52 +/-3	72.9	13455031
8	2	12	10	25	Transparent red	33	Yes	D 52 +/-3	72.9	14153953
8	2	12	10	50	Transparent red	33	Yes	D 52 +/-3	72.9	14170027
8	2	12	10	200	Transparent red	33	Yes	D 52 +/-3	72.9	14170026
8	2	12	10	50	Transparent yellow	33	Yes	D 52 +/-3	72.9	14170009
8	2	12	10	200	Transparent yellow	33	Yes	D 52 +/-3	72.9	14170008
8	2	12	10	25	Transparent yellow	33	Yes	D 52 +/-3	72.9	14153943
8	2	12	10	50	Yellow	33	Yes	D 52 +/-3	72.9	12265036
9.8	2	14	10	50	Black	38	Yes	D 52 +/-3	91	12266324
9.8	2	14	10	50	Blue	38	Yes	D 52 +/-3	91	12266323
9.8	2	14	10	50	Natural	38	Yes	D 52 +/-3	91	12266325
11	2.5	16	10	100	Black	38	Yes	D 52 +/-3	123	12265001
11	2.5	16	10	50	Black	38	Yes	D 52 +/-3	123	11639946
11	2.5	16	10		Blue	38	Yes	D 52 +/-3	123	11639939
11	2.5	16	10	100	Blue	38	Yes	D 52 +/-3	123	12265008
11	2.5	16	10	50	Green	38	Yes	D 52 +/-3	123	12265033
11	2.5	16	10	100	Natural	38	Yes	D 52 +/-3	123	12265015

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

Internal diameter	Wall thickness	Outer diameter	Maximum operating pressure at 20 °C	Roller length	Colour	Minimum bending radius	FDA quality mark	Hardness	Weight per meter	Article
mm	mm	mm	bar	m		mm			g	
11	2.5	16	10	50	Natural	38	Yes	D 52 +/-3	123	11639937
11	2.5	16	10	50	Red	38	Yes	D 52 +/-3	123	12265029
11	2.5	16	10	50	Silver	38	Yes	D 52 +/-3	123	12265025
11	2.5	16	10	100	Silver	38	Yes	D 52 +/-3	123	12265022
11	2.5	16	10	50	Yellow	38	Yes	D 52 +/-3	123	12265037

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.