



SGL Carbon Graphite sealing sheet SIGRAFLEX HOCHDRUCK

Characteristics

Series: SIGRAFLEX
Type: HOCHDRUCK
Graphite purity: ≥99.85 %
Ash content %: ≤0.15 %
Insert material: RVS 316 L [1.4404]
Insert type: Foil
Number of inserts: 7
Temperature range: -200 / 450 °C
Max. pressure: 200 bar

Characteristics [2]

Suitable for medium: Refrigerants, Cryogenic, Air [compressed air], Biodiesel, Fuels, Lubricant, Hydrocarbons, Oil, Chlorine, gaseous [7782-50-5], Solvents, Low pressure steam, Natural gas, Weak Acids, Grease, Chlorine Water < 5% [7782-50-5], Food & Beverages, Weak Alkalies
Approval according to: EC1935/2004, BS6755, Blow out VDI2200, DVGW, FIRE-SAFE API 607, BAM

Thickness mm	Length mm	Width mm	Article
1	1500	1500	11803545
1.5	1000	1000	10016694
1.5	1500	1500	11136435
2	1500	1500	11136434
2	1000	1000	10016695
3	1000	1000	10016696
3	1500	1500	10016698
4	1000	1000	10016697

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.