



BÖHLER FOX CN 23/12 Mo-A high alloyed electrodes

Rutile coated electrode with an increased ferrite [FN ~ 20].

As a result, the weld metal is tear-resistant and particularly suited for welding difficult to weld steels, austenite-ferrite compounds and oplassingen of corrosion-resistant layers.

Diameter mm	Total length mm	ISO standard	AWS standard	Packaging	Article
2.5	350	E 23 12 2 L R 3 2	E 309MoL-17	195	12574980
3.2	350	E 23 12 2 L R 3 2	E 309MoL-17	125	12574981
4	350	E 23 12 2 L R 3 2	E 309MoL-17	90	12574982

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.