## PFERD Grinding stone arched SP hardness O

Mounted points in hardness O consist of pink aluminium oxide in a vitrified bond.

These tools are characterized by a very long tool life and good stock removal rate due to the combination of wear resistant grain and a hard bond.

The hardness O is particularly suited for use on edges and for deburring work on steel components.

- The maximum permitted rotational speed refers to the unsupported shank length of 10 mm

Lining material	Granulation	Diameter	Hardness	Length	Pin connection	Article
		mm		mm	mm	
						23429139
Aluminium oxide	46	8	0	16	3	23872197
Aluminium oxide	46	13	0	20	6	23872201
Aluminium oxide	60	20	0	32	6	23872206
Aluminium oxide	100	3	0	6	3	23429137
Aluminium oxide	100	5	0	10	3	23429138

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

PR\_RC0102\_0058\_EN\_22.05.2024