

PFERD Grinding stone, conical, KE hardness M



Mounted points in hardness M are manufactured from a grain mix of tough, dark red and easy-to-break-down, white aluminium oxide in a vitrified bond.

This grain combination leads to a good balance between stock removal rate and tool life.

The hardness M is the most universally used bond for work on steel and cast steel.

- The maximum permitted rotational speed refers to the unsupported shank length of 10 mm

Lining material	Granulation	Diameter mm	Hardness	Length mm	Pin connection mm	Article
	30	20			6	12489864
	46	10			6	23872240
		16			6	23872249
						14591700
Aluminium oxide	24	32	M	32	6	23872226
Aluminium oxide	30	25	M	45	6	23872255
Aluminium oxide	46	32	M	32	6	23872227
Aluminium oxide	60	20	M	32	6	23872233

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.